

Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) EP 0 579 545 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:
12.03.1997 Bulletin 1997/11

(51) Int Cl.⁶: G02F 1/1337

(21) Application number: 93401822.7

(22) Date of filing: 15.07.1993

(54) Liquid crystal display device

Flüssigkristallanzeigevorrichtung

Dispositif d'affichage à cristal liquide

(84) Designated Contracting States:
DE FR GB IT SE

(30) Priority: 17.07.1992 US 916169

(43) Date of publication of application:
19.01.1994 Bulletin 1994/03

(73) Proprietor: MINNESOTA MINING AND
MANUFACTURING COMPANY
St. Paul, Minnesota 55133-3427 (US)

(72) Inventor: Radcliffe, Marc D.,
c/o Minnesota Mining and
St. Paul, Minnesota 55133-3427 (US)

(74) Representative: Warcoin, Jacques
Cabinet Régimbeau,
26, avenue Kléber
75116 Paris (FR)

(56) References cited:
EP-A- 0 255 236 EP-A- 0 266 136
EP-A- 0 360 521 GB-A- 2 026 190
GB-A- 2 144 232

- DATABASE WPI Week 8630, Derwent
Publications Ltd., London, GB; AN 86-194853
- DATABASE WPI Week 8219, Derwent
Publications Ltd., London, GB; AN 82-38520E

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 0 579 545 B1

Summary of the Invention

The present invention, in one aspect, relates to a bistable ferroelectric liquid crystal display device comprising a first substrate, a second substrate opposed to said first substrate, said substrates disposed to provide a non-helical alignment of the ferroelectric liquid crystal material and electrodes on said substrates to define one or a plurality of pixels, said electrode bearing first substrate having an aliphatic polyamide or polyester alignment coating thereon and said electrode bearing second substrate having an organosilsesquioxane polymer coating thereon, and a ferroelectric liquid crystal mixture comprising compounds having fluorinated tail portions disposed between said substrates, with the proviso that at least one substrate is transparent.

The devices of the invention provide high quality homogeneous alignment for the mixtures comprising compounds having fluorinated tail portions.

The present invention, in another aspect, provides a method for providing an aligned ferroelectric liquid crystal display device comprising

- 1) coating a first substrate bearing at least one electrode with a solution of aliphatic polyamide or polyester material;
- 2) curing said coating on the first substrate;
- 3) rubbing said coating to align said polyamide or polyester;
- 4) coating a second substrate bearing at least one electrode with a solution of organosilsesquioxane polymer;
- 5) curing said coating on the second substrate;
- 6) placing said substrates with coated faces in opposing position and disposed to provide a non-helical alignment of a ferroelectric liquid crystal material when said liquid crystal material is placed between said coated substrates;
- 7) securing said so disposed substrates, with the proviso that at least one of said substrates is transparent.

Brief Description of the Drawing

The FIG. is a schematic sectional view of a liquid crystal device according to the present invention.

Detailed Description of the Invention

Ferroelectric liquid crystal devices such as described by Clark et al. in U.S. Patents No. 4,363,059 and No. 4,367,924, are generally bi-stable or two level devices. The two level devices are binary in nature, each picture element, or pixel, is either wholly transmitting or absorbing.

In a surface stabilized device, the liquid crystal molecules exist in either of two states in their lowest energy configuration, and both states can be accessed by the polarity of the applied field. This is accomplished by using an alignment layer on at least one of the substrates (or boundary plane) and making the spacing of the substrates of the cell less than the chiral pitch length of the liquid crystal molecule, so that the surface forces can completely unwind the molecular chiral helix.

The fixed molecular tilt angle and the boundary plane of the substrate dictate that there are two possible configurations of the molecules. In one configuration the polarization vector points towards one boundary plane, and in the other configuration, the polarization vector points towards the other boundary plane. These two states are the bi-stable states of the device. The application of an electric field across the device will switch liquid crystal molecules from one state to the other, but the molecules will always seek their lowest energy configuration. With the molecular helixes unwound, the molecular movement from one state to another is along a path described by a cone with the apex and center line parallel to the smectic layer normal. The two stable states of the molecule are at either low energy site on this cone.

When a voltage is applied across any liquid crystal device, the liquid crystal material within the device experiences electric field forces from two sources. One force, from the spontaneous polarization is proportional to

$$\vec{P} \cdot \vec{E},$$

and is linear with the electric field, and a second force arising from the anisotropy in the dielectric permittivity, $\Delta\epsilon E^2$ which varies quadratically with the electric field. In the above expressions, P is the polarization, $\Delta\epsilon$ is the dielectric anisotropy of the liquid crystal material, and E is the electric field developed across the device as a result of the applied voltage. In such ferroelectric devices, the




term is non-zero and is the dominating term, and bi-stable switching occurs.


The liquid crystal materials found most advantageous for use in the present invention are fluorinated chiral liquid crystal materials such as described, for example in U.S. Patent No. 4,886,619 (Janulis) and U.S. Patent No. 5,082,587 (Janulis), which are incorporated herein by reference. These materials can be used by themselves or in mixtures with other fluorinated chiral or achiral materials or hydrocarbon materials.

As can be seen in the FIG., device 10 of the present invention comprises two opposing substrates 11, 11', at least one of which is optically transparent. The inward facing surfaces of each substrate 11, 11' contains electrically conductive electrodes 12, 12' in a configuration to produce a desired pattern, electrodes 12, 12' on the substrates being transparent. Electrodes 12, 12' may be of any electrically conductive material, a common one being indium tin oxide, and may be applied by methods commonly known in the art. Substrate 11 has thereon alignment coating or layer 14 of an aliphatic polyamide or polyester material which has been rubbed and substrate 11' has thereon layer 16 of organosilsesquioxane polymer. Opposed substrates 11, 11' are disposed a small distance apart with spacers 18, said distance, along with the alignment layer, allowing for the non-helicoidal alignment of the included liquid crystal material 20. The so-produced device is then filled with liquid crystal material 20 as heretofore described, and the electrodes connected to an appropriate electrical driving source.


The aliphatic polyamide material or the polyester material serves as an alignment or ordering substance. Such polyamide materials include any of the various nylons such as, for example,




nylon 6





nylon 6/6



nylon 11




nylon 12



Also, nylon copolymers such as ELVAMID 8064, a terpolymer available from DuPont Company, can be used as the alignment layer. Mixtures of the polyamide materials may also be used.

Polyester materials useful in the present invention include, for example, poly(ethylene terephthalate)




poly(butylene terephthalate) and poly(hexylene terephthalate).

The polyester or polyamide alignment layer is preferably 100 to 10,000 Å thick, more preferably 200 to 1000 Å thick, most preferably 400 to 600 Å thick. The alignment layer is preferably of uniform thickness. The layer may be deposited by conventional techniques such as spin coating, dip coating, roller coating or spraying.

The polyester or polyamide alignment layer is aligned prior to utilization in a cell by techniques well-known to those skilled in the art such as by rubbing with fabric to propagate a zone of plastic deformation and realignment of the polymer chains.

The organosilsesquioxane polymer layer of the present invention may be rubbed or non-rubbed. Typical organosilsesquioxane polymers have pendant moieties such as, for example, hydrogen atoms, alkyl groups having 1 to 4 carbon atoms, such as methyl or ethyl groups, phenyl or substituted phenyl groups such as xylyl or tolyl groups, or vinyl groups and have functional groups such as, for example, hydroxy, methoxy, ethoxy or chloro groups. Preferred organosilsesquioxane polymers are methylsilsesquioxane polymer (Resin GR-651L, available from Owens-Illinois, Inc.) and methyl-phenylsilsesquioxane polymer (Resins GR-100 and GR-150, available from Owens-Illinois, Inc.). Particularly preferred is methylsilsesquioxane polymer which can be represented by the idealized structure



The organosilsesquioxane alignment layer is preferably 100 to 10,000 Å thick, more preferably 200 to 1000 Å thick, most preferably 300 to 600 Å thick. The alignment layer is preferably of uniform thickness. The layer may be deposited by conventional techniques such as spin coating, dip coating, roller coating or spraying.

Additional optional layers may also be present. Such layers can include an adhesion promoting layer and/or an

insulating layer coated on the electrode bearing substrate prior to application of the alignment layer. Commercially available adhesion promoting materials include, for example, bis[3-(triethoxysilyl)-propyl]amine and VM651, a γ -aminopropyltriethoxysilane available from DuPont Company. Typical insulating layers may be formed from SiO_2 , TiO_2 or Ta_2O_5 at a thickness of about 200 to 1000 Å.

The devices of the present invention can be, for example, in the form of transmissive devices where the opposed substrate is transparent, reflective devices where the opposed substrate is reflective, and devices using dyes mixed with the ferroelectric liquid crystal material which exhibit the guest-host effect, all of which are well-known to those skilled in the art.

In the following nonlimiting examples, all temperatures are in degrees Centigrade and all parts and percentages are by weight unless indicated otherwise. In each example, the electrodes of the cell were connected to an arbitrary waveform generator with variable output voltage. Optical transmission was measured by placing the cell on a rotating stage between two crossed polarizers with the polarizer/cell combination placed between a collimated light source of about 1 mW intensity and about 5 mm diameter and a silicon photodetector, the output of which was monitored on an oscilloscope. The light, obtained from an incandescent source, was filtered to confine the wavelength spectrum between 450 and 700 nm.

The 5-hexyl-2-(4-(1,1-dihydroperfluoro-2-(2-butoxyethoxy)ethoxy)phenyl)pyrimide used in the examples was prepared by fluorination and methanolysis of butoxyethoxyethyl acetate to provide methyl perfluoro-2-(butoxyethoxy)acetate which was then reduced with sodium borohydride to provide 1,1-dihydroperfluoro-2-(butoxyethoxy)ethanol. The 1,1-dihydroperfluoro-2-(butoxyethoxy)ethanol was then converted to its triflate by reaction with triflic anhydride and triethylamine. The resulting triflate was then coupled with 5-hexyl-2-(4-hydroxyphenyl)pyrimidine by triflate displacement reaction. The 5-octyl-2-(4-(1,1-dihydroperfluoro-2-(2-butoxyethoxy)ethoxy)phenyl)-pyrimidine was prepared in the same manner as the 5-hexyl-2-(4-(1,1-dihydroperfluoro-2-(2-butoxyethoxy)ethoxy)phenyl)pyrimide except 5-octyl-2-(4-hydroxyphenyl)pyrimidine was substituted for the 5-hexyl-2-(4-hydroxyphenyl)pyrimidine.

The cells of each example were tested using the following procedures.

Memory Angle

The cell was driven with a voltage waveform of alternating bipolar pulses of 20 V/ μm amplitude spaced 30 mS apart. The cell was aligned between crossed polarizers to obtain the best extinction during the negative half-cycle of the square wave. The cell was then aligned to obtain the best extinction during the positive half-cycle of the square wave. The angle separating the extinction points of the two memory states is the memory angle, $2\phi_m$.

$$\phi_m/\phi_t$$

The cell was driven with a 30 Hz square wave of 20 V/ μm amplitude. The cell was aligned between crossed polarizers to obtain the best extinction during the negative half-cycle of the waveform. The cell was then aligned to obtain the best extinction during the positive half-cycle of the square wave. The angle separating extinction points of the two driven states is the tilt angle, $2\phi_t$. The ratio memory angle/tilt angle, $2\phi_m/2\phi_t$, is reported.

Latching Time

The cell was driven with a voltage waveform of alternating bipolar pulses of 20 V/ μm amplitude spaced 30 mS apart. The cell was aligned between crossed polarizers to obtain the best extinction during the negative half-cycle of the waveform. Then the cell was driven with a waveform of bipolar pulses of 20 V/ μm amplitude spaced 30 mS apart by a train of square wave pulses 30 mS wide and 6.7 V/ μm amplitude. The minimum pulse width needed to observe two stable and saturated memory states is the latching time.

Contrast Ratio

The cell was driven with a 30 Hz square wave of 20 volt amplitude. The cell was aligned between crossed polarizers to obtain the best extinction during the negative half-cycle of the square wave. The ratio of the transmitted light intensity during the positive and negative half-cycles of the square wave was obtained. The cell was then aligned to obtain the best extinction during the positive half-cycle of the square wave and the transmitted light ratio was again determined. The average of the two ratios is reported as the contrast ratio.

Bias Contrast Ratio

The cell was driven with a waveform of alternating bipolar pulses of 20 V/ μm amplitude spaced 30 mS apart by a

train of square pulses 30 mS wide and 6.7 V/ μ m amplitude. The cell was aligned between crossed polarizers to obtain the best extinction states. Set at the first angle, the cell was driven by a waveform of bipolar pulses at 20 V/ μ m and spaced 30 mS apart by a train of square wave pulses 30 mS wide and 6.7 V/ μ m amplitude. The transmitted light intensity is determined. Then the sign of the bipolar pulse field was inverted and the transmitted intensity determined.

5 This contrast ratio is averaged with the analogous value obtained similarly for the other angle memory state to obtain the bias contrast ratio.

Example 1

10 Onto a patterned indium tin oxide coated glass substrate (2.85 cm wide, 3.5 cm long, 0.1 cm thick, cut from PD-5005 available from Donnelly Corp.) which had been ultrasonically cleaned were placed several drops of 0.52 weight percent solution of nylon 6/6 [poly(hexamethylene adipamide), No. 18,112-9, available from Aldrich Chemical Co. Inc.] in formic acid. The substrate was spun at 1200 rpm for 40 seconds and cured at 75°C for 16 hours to provide a coating about 400 Å thick. The coated substrate was rubbed 20 strokes in one direction with a 115 gram rubbing bar (a glass

15 rod 2.5 cm in diameter, 10 cm long) about which a velveteen fabric (#5100 Matinee, 65/35 cotton/rayon, available from J.B. Martin Co.) with the pile side out was tightly wrapped, to provide an oriented alignment layer on the substrate.

Onto an indium tin oxide coated glass substrate (2.85 cm wide, 3.5 cm long, 0.1 cm thick, PD-5005 available from Donnelly Corp.) having spacer posts 1.5 microns in height, and which had been ultrasonically cleaned were placed several drops of 1.5 weight percent solution of methylsilsesquioxane polymer (5.6% GR-651L, available from Owens-Illinois, Inc.) in butyl alcohol. The substrate was spun at 8000 rpm for 20 seconds and cured at 75°C for 16 hours to provide a alignment coating about 200-300 Å thick.

20 The substrates were assembled with the alignment layers facing inward to form a cell using UV curable adhesive (Norland 61 Optical Adhesive, available from Norland Products Inc.). The cell was then filled with a liquid crystal mixture using capillary filling under vacuum by heating to 100°C. The mixture contained the following components:

25

76.5%	5-octyl-2-(4-(1,1-dihydroperfluoro-2-(2-butoxyethoxy)ethoxy)phenyl)-pyrimidine
4.5%	5-octyl-2-(4-(1,1-dihydroperfluorooctyloxy)phenyl)pyrimidine
4.5%	5-nonyl-2-(4-(1,1-dihydroperfluorooctyloxy)phenyl)pyrimidine
4.5%	5-decyl-2-(4-(1,1-dihydroperfluorooctyloxy)phenyl)pyrimidine
30 10.0%	(S)-4-(2-chloro-4-methylpentanoyloxy)phenyl 4-(1,1-dihydroperfluorobutoxy)benzoate.

The transition temperatures upon cooling from the isotropic state (I) to the crystalline state (K) were I-SmA: 73°C, SmA-SmC*: 30°C and SmC*-K: <-10°C.

35 The cell exhibited excellent alignment of the liquid crystal mixture as determined by observation of the liquid crystal texture with a polarizing microscope, and was evaluated for latching speed, memory angle, ϕ_m/ϕ_i , contrast ratio and bias contrast ratio. The results are as set forth in Table 1. The cell exhibited indefinitely stable switched states that remained undisrupted when the electrodes were shunted together.

40 Example 2

A liquid crystal display device was prepared as in Example 1 except the liquid crystal mixture contained the following components

45

12.44%	5-hexyl-2-(4-(1,1-dihydroperfluoro-2-(2-butoxyethoxy)ethoxy)phenyl)pyrimide
20.74%	5-octyl-2-(4-(1,1-dihydroperfluorohexyloxy)phenyl)pyrimidine
20.74%	5-nonyl-2-(4-(1,1-dihydroperfluorohexyloxy)phenyl)pyrimidine
20.74%	5-decyl-2-(4-(1,1-dihydroperfluorohexyloxy)phenyl)pyrimidine
8.30%	5-decyl-2-(4-(1,1-dihydroperfluorobutoxy)phenyl)pyrimidine
50 7.21%	(S)-4-(2-chloro-4-methylpentanoyloxy)phenyl 4-(1,1-dihydroperfluorobutoxy)benzoate
3.25%	2,3-dicyano-4-octyloxyphenyl 4-(1,1-dihydroperfluorohexyloxy)benzoate
6.58%	2,3-difluoro-4-octyloxyphenyl 4-(1,1-dihydroperfluorohexyloxy)benzoate

55 The transition temperatures upon cooling from the isotropic state (I) to the crystalline state (K) were I-SmA: 78°C, SmA-SmC*: 59°C and SmC*-K: 12°C.

The cell exhibited very good alignment of the liquid crystal mixture as determined by observation of the liquid crystal texture with a polarizing microscope, and was evaluated for latching speed, memory angle, ϕ_m/ϕ_i , contrast ratio

and bias contrast ratio. The results are as set forth in Table 1.

Example 3

A liquid crystal display device was prepared as in Example 1 except the liquid crystal mixture contained the following components

13.80%	5-hexyl-2-(4-(1,1-dihydroperfluoro-2-(2-butoxyethoxy)ethoxy)phenyl)pyrimide
23.00%	5-octyl-2-(4-(1,1-dihydroperfluorohexyloxy)phenyl)pyrimidine
23.00%	5-nonyl-2-(4-(1,1-dihydroperfluorohexyloxy)phenyl)pyrimidine
23.00%	5-decyl-2-(4-(1,1-dihydroperfluorohexyloxy)phenyl)pyrimidine
9.20%	5-decyl-2-(4-(1,1-dihydroperfluorobutoxy)phenyl)pyrimidine
8.00%	(S)-4-(2-chloro-4-methylpentanoyloxy)phenyl 4-(1,1-dihydroperfluorobutoxy)benzoate

The transition temperatures upon cooling from the isotropic state (I) to the crystalline state (K) were I-SmA: 81°C, SmA-SmC*: 54°C and SmC*-K: 10°C.

The cell exhibited very good, highly uniform alignment of the liquid crystal mixture as determined by observation of the liquid crystal texture with a polarizing microscope. The device was evaluated for latching speed, memory angle, ϕ_m/ϕ_t contrast ratio and bias contrast ratio. The results are as set forth in Table 1.

Example 4

A liquid crystal display device was prepared as in Example 3 except a polyamide terpolymer (ELVAMIDE 8064 available from DuPont Company) was substituted for the nylon 6/6.

The cell exhibited very good alignment of the liquid crystal mixture as determined by observation of the liquid crystal texture with a polarizing microscope. The device was evaluated for latching speed, memory angle, ϕ_m/ϕ_t and contrast ratio. The results are set forth in Table 1.

Comparative Example C1

A liquid crystal display device was prepared as in Example 3 except polytrimethyl hexamethylene terephthalamide (#331, an aromatic polyamide available from Scientific Polymer Products) was substituted for the nylon 6/6, the solvent used was 60:40 *m*-cresol:methanol and the curing temperature was 65°C.

The cell exhibited poor quality alignment due to occasional nucleation of disordered focal conic domains in the liquid crystal mixture as determined by observation of the liquid crystal texture with a polarizing microscope. The device was evaluated for latching speed, memory angle, ϕ_m/ϕ_t and contrast ratio. The results are set forth in Table 1.

Comparative Example C2

A liquid crystal display device was prepared as in Example 3 except ZYTEL FE-3303 (high Tg aromatic polyamide copolymer available from DuPont Company) was substituted for the nylon 6/6, and the solvent used was 60:40 *m*-cresol:methanol.

The cell exhibited poor quality alignment due to nucleation of disordered focal conic domains in the liquid crystal mixture as determined by observation of the liquid crystal texture with a polarizing microscope. The device was evaluated for latching speed, memory angle, ϕ_m/ϕ_t and contrast ratio. The results are as set forth in Table 1.

Example 5

A liquid crystal display device was prepared as in Example 1 except the liquid crystal mixture contained the following components

90%	5-octyl-2-(4-(1,1-dihydroperfluoro-2-(2-butoxyethoxy)ethoxy)phenyl)-pyrimidine
10%	5-octyl-2-(4-((S)-(2-chloro-4-methylpentanoyloxy)phenyl)pyrimidine

The transition temperatures upon cooling from the isotropic state (I) to the crystalline state (K) were I-SmA: 76°C, SmA-SmC*: 30°C and SmC*-K: <-10°C.

The cell exhibited very good alignment of the liquid crystal mixture as determined by observation of the liquid crystal texture with a polarizing microscope. The device was evaluated as in Example 1. The results are set forth in Table 1. The cell exhibited long-lived stable switched states that remained undisrupted when the electrodes were shunted together.

Comparative Example C3

A liquid crystal display device was prepared as in Example 5 except nylon 6/6 was substituted for the methylsilsesquioxane polymer. Both coated substrates were rubbed to generate a parallel alignment orientation.

The cell exhibited poor alignment of the liquid crystal mixture as determined by observation of the liquid crystal texture with a polarizing microscope. The device was evaluated as in Example 1. The results are as set forth in Table 1.

Comparative Example C4

A liquid crystal display device was prepared as in Example 5 except a polyimide (RN-779 available from Nissan Chemical Industries Ltd.) diluted to 50% of its original concentration with the supplied solvent was substituted for both the nylon 6/6 and methylsilsesquioxane polymer. PYRALIN VM-651, 0.05% in 95% ethanol, silane adhesion promoter (available from DuPont) was coated on the substrate prior to the application of the polyimide solution. The substrate was spun at 6000 rpm for 30 seconds and cured at 180°C for 1 hour. Both films were rubbed to generate a parallel alignment orientation.

The cell exhibited fair alignment of the liquid crystal mixture with spots, streaks and zig-zag bands as determined by observation of the liquid crystal texture with a polarizing microscope. The device was evaluated as in Example 1. The results are set forth in Table 1.

Comparative Example C5

A liquid crystal display device was prepared as in Example 5 except a polyimide (RN-779 available from Nissan Chemical Industries Ltd.) diluted to 50% of its original concentration with the supplied solvent was substituted for the nylon 6/6. PYRALIN VM-651, 0.05% in 95% ethanol, silane adhesion promoter (available from DuPont) was coated on the substrate prior to the application of the polyimide solution. The substrate was spun at 6000 rpm for 30 seconds and cured for 1 hour at 180°C.

The cell exhibited poor, i.e., focal conic, alignment of the liquid crystal mixture as determined by observation of the aligned texture with a polarizing microscope.

Comparative Example C6

A liquid crystal display device was prepared as in Example 5 except polystyrene was substituted for the methylsilsesquioxane polymer.

The cell exhibited poor, i.e., focal conic, alignment of the liquid crystal mixture as determined by observation of the liquid crystal texture with a polarizing microscope.

Comparative Example C7

A liquid crystal display device was prepared as in Example 1 except a polyamide terpolymer (ELVAMIDE 8064 available from DuPont Company) was substituted for the nylon 6/6 and 1.5 micron posted indium-tin oxide (ITO) coated glass was used in place of the methylsilsesquioxane coated ITO glass with 1.5 micron posts, and the liquid crystal mixture contained the following components

15%	5-hexyl-2-(4-(1,1-dihydroperfluoro-2-(2-butoxyethoxy)ethoxy)phenyl)pyrimide
25%	5-octyl-2-(4-(1,1-dihydroperfluorohexyloxy)phenyl)pyrimidine
50%	5-decyl-2-(4-(1,1-dihydroperfluorohexyloxy)phenyl)pyrimidine
10%	(S)-4-(2-chloro-4-methylpentanoyloxy)phenyl 4-(1,1-dihydroperfluorobutoxy)benzoate

The transition temperatures upon cooling from the isotropic state (I) to the crystalline state (K) were I-SmA: 81°C, SmA-SmC*: 54°C and SmC*-K: >10°C.

The cell exhibited good to fair alignment of the liquid crystal mixture with some domain boundary walls present as determined by observation of the liquid crystal texture with a polarizing microscope. The device was evaluated for

latching speed, memory angle, contrast ratio and ϕ_m/ϕ_t . The results are as set forth in Table 1.

Example 6

A liquid crystal display device was prepared as in Example 1 except a silane adhesion promoter (PYRALIN VM-651 available from DuPont, 0.05% in 95% ethanol) was coated on the substrate prior to application of the alignment layer. Poly(ethylene terephthalate) (PET, Cat. No. 20,025-5, available from Aldrich Chemical Co., Inc.) was substituted for the nylon 6/6 and the solvent used was o-chlorophenol. The substrate was spun at 2000 rpm for 30 seconds and cured for 16 hours at 75°C.

The cell exhibited good alignment as determined by observation of the liquid crystal texture with a polarizing microscope. The device was evaluated as in Example 1. The results are set forth in Table 1.

Example 7

A liquid crystal display device was prepared as in Example 1 except a 2:1 methyl-phenylsilsesquioxane (GR-100, available from Owens-Illinois, Inc.), 3% in butanol, was substituted for the methylsilsesquioxane. PYRALIN VM-651 silane adhesion promoter, 0.05% in 95% ethanol, was coated on the substrate prior to the application of the alignment layer. The substrate was spun at 6000 rpm for 20 seconds and cured for 1/2 hours at 250°C.

The cell exhibited good alignment as determined by observation of the liquid crystal texture with a polarizing microscope. The device was evaluated as in Example 1. The results are set forth in Table 1.

Example 8

A liquid crystal display device was prepared as in Example 1 except a 1:1 methyl-phenylsilsesquioxane (GR-150, available from Owens-Illinois, Inc.), 3% in butanol, was substituted for the methylsilsesquioxane. PYRALIN VM-651 silane adhesion promoter, 0.05% in 95% ethanol, was coated on the substrate prior to the application of the alignment layer. The substrate was spun at 6000 rpm for 20 seconds and cured for 1/2 hours at 250°C.

The cell exhibited good alignment as determined by observation of the liquid crystal texture with a polarizing microscope. The device was evaluated as in Example 1. The results are set forth in Table 1.

Comparative Example C8

A liquid crystal display device was prepared as in Comparative Example C7 except polydimethylphenylene oxide was substituted for the ELVAMIDE and the solvent used was 1-chloroaphthalene. The substrate was spin coated at 1200 rpm for 2 minutes and cured at 70°C for 1 hour.

The device was examined with a polarizing microscope for alignment uniformity. No alignment was observed.

Comparative Example C9

A liquid crystal display device was prepared as in Comparative Example C7 except a polyimide (RN-715 available from Nissan Chemical Industries, Ltd.) diluted to 10% of its original concentration with cyclohexanone was substituted for the ELVAMIDE. The substrate was spun at 1200 rpm for 2 minutes and cured at 80°C for 16 hours.

The device was examined with a polarizing microscope for alignment uniformity. No alignment was observed.

Example 9

A liquid crystal display device was prepared as in Example 1 except the liquid crystal mixture contained 20% ZLI-4237 (available from Merck, EM Industries) and 80% of the mixture of Example 3. The transition temperatures upon cooling from the isotropic state (I) to the crystalline state (K) were I=SmA: 87°C, SmA-SmC: 35°C and SmC-K: <-10°C.

The cell exhibited good alignment of the liquid crystal mixture as determined by observation of the liquid crystal texture with a polarizing microscope.

Comparative Example C10

A liquid crystal display device was prepared as in Comparative Example 4 except the polyimide was replaced by another polyimide (RN-763 available from Nissan Chemical Industries Ltd.) diluted to 50% of its original concentration with 4 parts γ -butyrolactone and 1 part butyl cellosolve, and the liquid crystal mixture was the same as in Example 9. PYRALIN VM-651, 0.05% in 95% ethanol, silane adhesion promoter (available from DuPont) was coated on the sub-

strate prior to the application of the polyimide solution. The substrate was spun at 6000 rpm for 60 seconds and cured at 80°C for 15 minutes and 120°C for 1 hour.

The cell exhibited poor, i.e., focal conic, alignment of the liquid crystal mixture as determined by observation of the aligned texture with a polarizing microscope.

Comparative Example C11

A liquid crystal display device was prepared as in Comparative Example 10 and the liquid crystal mixture was the same as in Example 3.

The cell exhibited poor, i.e., focal conic, alignment of the liquid crystal mixture as determined by observation of the aligned texture with a polarizing microscope.

Comparative Example C12

A liquid crystal display device was prepared as in Example 3 except a polyimide (RN-763, available from Nissan Chemical Industries Ltd.) diluted to 50% of its original concentration with 4 parts γ -butyrolactone and 1 part butyl cellosolve was substituted for the nylon 6/6. PYRALIN VM-651, 0.05% in 95% ethanol, silane adhesion promoter (available from DuPont) was coated on the substrate prior to the application of the polyimide solution. The substrate was spun at 6000 rpm for 60 seconds and cured at 80°C for 15 minutes and 120°C for 1 hour.

The cell exhibited poor, i.e., focal conic, alignment of the liquid crystal mixture as determined by observation of the aligned texture with a polarizing microscope.

TABLE 1

Example	Memory Angle ($2\phi_m$)	$2\phi_m/2\phi_t$	Latching Time (μ S)	Contrast Ratio	Bias Contrast Ratio
1	38	0.86	31	2200	38
2	28	0.56	33	380	10
3	35	0.56	80	640	1.7
4	36	0.58	80	300	--
C1	33	0.53	80	300	--
C2	30	0.48	300	70	--
5	34	0.92	9	--	140
C3	30	0.75	10	740	35
C4	30	0.75	12	560	55
C7	37	0.60	60	100	--
6	39	0.87	36	1300	21
7	37	0.84	28	573	33
8	37	0.82	24	475	23

Various modifications and alterations of this invention will become apparent to those skilled in the art without departing from the scope of this invention as claimed and it should be understood that this invention is not to be unduly limited to the illustrative embodiments set forth herein.

Claims

1. A bistable ferroelectric liquid crystal display device comprising a first substrate, a second substrate opposed to said first substrate, said substrates disposed to provide a non-helicoidal alignment of the ferroelectric liquid crystal material and electrodes on said substrates to define one or a plurality of pixels, said electrode bearing first substrate having an aliphatic polyamide or polyester alignment coating thereon and said electrode bearing second substrate having an organosilsesquioxane polymer coating thereon, and a ferroelectric liquid crystal mixture comprising compounds having fluorinated tail portions disposed between said substrates with the proviso that at least one of said substrates is transparent.
2. The device of claim 1 wherein said polyamide coating is nylon.

3. The device of claim 1 wherein said polyester coating is poly(ethylene terephthalate), poly(butylene terephthalate) or poly(hexylene terephthalate).
4. The device of claim 1 wherein said organosilsesquioxane polymers have pendant moieties selected from hydrogen atoms, alkyl groups having 1 to 4 carbon atoms, phenyl groups, substituted phenyl groups or vinyl groups and functional groups selected from hydroxy, methoxy, ethoxy or chloro groups or mixtures thereof.
5. The device of claim 1 wherein both said first substrate and said second substrate are transparent.
6. A method for providing an aligned ferroelectric liquid crystal display device comprising
 - 1) coating a first substrate bearing at least one electrode with a solution of aliphatic polyamide material or polyester material;
 - 2) curing said coating on said first substrate;
 - 3) rubbing said coating to align said polyamide or polyester;
 - 4) coating a second substrate bearing at least one electrode with a solution of organosilsesquioxane polymer;
 - 5) curing said coating on said second substrate;
 - 6) placing said substrates with coated faces in opposing position and disposed to provide a non-helical alignment of a ferroelectric liquid crystal material when said liquid crystal material is placed between said coated substrates;
 - 7) securing said so disposed substrates, with the proviso that at least one of said substrates is transparent.
7. The method of claim 6 wherein said polyamide coating is nylon.
8. The method of claim 6 wherein said polyester coating is poly(ethylene terephthalate), poly(butylene terephthalate) or poly(hexylene terephthalate).
9. The method of claim 6 wherein said organosilsesquioxane polymers have pendant moieties selected from hydrogen atoms, alkyl groups having 1 to 4 carbon atoms, phenyl groups, substituted phenyl groups or vinyl groups and functional groups selected from hydroxy, methoxy, ethoxy or chloro groups or mixtures thereof.
10. The method of claim 6 wherein both said first substrate and said second substrate are transparent.

Patentansprüche

1. Bistabile, ferroelektrische Flüssigkristall-Anzeigevorrichtung, umfassend ein erstes Substrat, ein zweites Substrat, das dem ersten Substrat gegenüberliegt, wobei die Substrate so angeordnet sind, daß eine nicht-schraubenförmige Ausrichtung des ferroelektrischen Flüssigkristall-Materials und der Elektroden auf den Substraten bereitgestellt wird, um einen Pixel oder eine Mehrzahl von Pixeln zu definieren, wobei das die Elektrode tragende erste Substrat eine Ausrichtungsbeschichtung eines aliphatischen Polyamids oder Polyesters darauf aufweist, und das die Elektrode tragende zweite Substrat eine Organosilsesquioxan-Polymerbeschichtung darauf aufweist, und eine ferroelektrische Flüssigkristall-Mischung, umfassend Verbindungen mit fluorierten Schwanzanteilen, die zwischen den Substraten angeordnet sind, mit der Maßgabe, daß wenigstens eines der Substrate transparent ist.
2. Vorrichtung gemäß Anspruch 1, worin die Polyamidbeschichtung Nylon ist.
3. Vorrichtung gemäß Anspruch 1, worin die Polyesterbeschichtung Poly(ethylenterephthalat), Poly(butylenterephthalat) oder Poly(hexylenterephthalat) ist.
4. Vorrichtung gemäß Anspruch 1, worin die Organosilsesquioxan-Polymere seitliche Struktureinheiten aufweisen, die aus Wasserstoffatomen, Alkylgruppen mit 1 bis 4 Kohlenstoffatomen, Phenylgruppen, substituierten Phenylgruppen oder Vinylgruppen und funktionellen Gruppen, ausgewählt aus Hydroxy-, Methoxy-, Ethoxy- oder Chlorgruppen, oder Mischungen derselben ausgewählt sind.
5. Vorrichtung gemäß Anspruch 1, worin sowohl das erste Substrat als auch das zweite Substrat transparent sind.
6. Verfahren zur Bereitstellung einer ausgerichteten, ferroelektrischen Flüssigkristall-Anzeigevorrichtung, umfas-

send:

- 1) das Beschichten eines ersten Substrats, das wenigstens eine Elektrode trägt, mit einer Lösung von aliphatischem Polyamid-Material oder Polyester-Material;
 - 2) das Härten der Beschichtung auf dem ersten Substrat;
 - 3) das Reiben der Beschichtung, um das Polyamid oder den Polyester auszurichten;
 - 4) das Beschichten eines zweiten Substrats, das wenigstens eine Elektrode trägt, mit einer Lösung von Organosilsesquioxan-Polymer;
 - 5) das Härten der Beschichtung auf dem zweiten Substrat;
 - 6) das Anordnen der Substrate mit beschichteten Oberflächen in sich gegenüberstehender Lage und auf derartige Weise, daß eine nicht-schraubenförmige Ausrichtung eines ferroelektrischen Flüssigkristall-Materials bereitgestellt wird, wenn das Flüssigkristall-Material zwischen den beschichteten Substraten angeordnet wird;
 - 7) das Befestigen der so angeordneten Substrate, mit der Maßgabe, daß wenigstens eines der Substrate transparent ist.
7. Verfahren gemäß Anspruch 6, worin die Polyamidbeschichtung Nylon ist.
 8. Verfahren gemäß Anspruch 6, worin die Polyesterbeschichtung Poly(ethylenterephthalat), Poly(butylenterephthalat) oder Poly(hexylenterephthalat) ist.
 9. Verfahren gemäß Anspruch 6, worin die Organosilsesquioxan-Polymere seitliche Struktureinheiten aufweisen, die aus Wasserstoffatomen, Alkylgruppen mit 1 bis 4 Kohlenstoffatomen, Phenylgruppen, substituierten Phenylgruppen oder Vinylgruppen und funktionellen Gruppen, ausgewählt aus Hydroxy-, Methoxy-, Ethoxy- oder Chlorgruppen, oder Mischungen derselben ausgewählt sind.
 10. Verfahren gemäß Anspruch 6, worin sowohl das erste Substrat als auch das zweite Substrat transparent sind.

Revendications

1. Dispositif d'affichage à cristaux liquides ferroélectriques bistables comprenant un premier substrat, un second substrat opposé audit premier substrat, lesdits substrats étant disposés de façon à fournir un alignement non hélicoïdal du matériau cristal liquide ferroélectrique, et des électrodes sur lesdits substrats pour définir un ou plusieurs pixels, ledit premier substrat portant une électrode étant recouvert d'un revêtement d'alignement en polyester ou polyamide aliphatique, et ledit second substrat portant une électrode étant recouvert d'un revêtement de polymère organosilsesquioxane, et un mélange de cristaux liquides ferroélectriques comprenant des composés contenant des portions d'extrémité fluorées placé entre lesdits substrats, à condition qu'au moins un desdits substrats soit transparent.
2. Dispositif de la revendication 1, dans lequel ledit revêtement de polyamide est du nylon.
3. Dispositif de la revendication 1, dans lequel ledit revêtement de polyester est du poly(éthylène-téréphtalate), du poly(butylène-téréphtalate) ou du poly(hexylène-téréphtalate).
4. Dispositif de la revendication 1, dans lequel lesdits polymères organosilsesquioxanes contiennent des groupements pendants choisis parmi les atomes d'hydrogène, les groupes alkyle comportant 1 à 4 atomes de carbone, les groupes phényle, les groupes phényle substitués ou les groupes vinyle et les groupes fonctionnels choisis parmi les groupes hydroxy, méthoxy, éthoxy ou chloro ou leurs mélanges.
5. Dispositif de la revendication 1, dans lequel ledit premier substrat et ledit second substrat sont tous deux transparents.
6. Procédé pour fournir un dispositif d'affichage à cristaux liquides ferroélectriques alignés comprenant les étapes consistant à:
 - 1) revêtir un premier substrat portant au moins une électrode d'une solution de matière polyamide aliphatique ou de matière polyester;
 - 2) durcir ledit revêtement sur ledit premier substrat;

- 3) frotter ledit revêtement pour aligner ledit polyamide ou polyester;
 - 4) revêtir un second substrat portant au moins une électrode d'une solution d'un polymère organosilsesquioxane;
 - 5) durcir ledit revêtement sur ledit second substrat;
 - 5 6) placer lesdits substrats de manière que les faces revêtues soient opposées l'une à l'autre et les disposer de façon à obtenir un alignement non hélicoïdal d'un matériau à cristal liquide ferroélectrique lorsque ledit matériau cristal liquide est placé entre lesdits substrats revêtus;
 - 7) fixer lesdits substrats ainsi disposés, à condition qu'au moins un desdits substrats soit transparent.
-
- 10 7. Procédé de la revendication 6, dans lequel ledit revêtement de polyamide est du nylon.
 8. Procédé de la revendication 6, dans lequel ledit revêtement de polyester est du poly(éthylène-téréphtalate), du poly(butylène-téréphtalate) ou du poly(hexylène-téréphtalate).
 - 15 9. Procédé de la revendication 6, dans lequel lesdits polymères organosilsesquioxanes contiennent des groupements pendants choisis parmi les atomes d'hydrogène, les groupes alkyle comportant 1 à 4 atomes de carbone, les groupes phényle, les groupes phényle substitués ou les groupes vinyle et les groupes fonctionnels choisis parmi les groupes hydroxy, méthoxy, éthoxy ou chloro ou leurs mélanges.
 - 20 10. Procédé de la revendication 6, dans lequel ledit premier substrat et ledit second substrat sont tous deux transparents.

25

30

35

40

45

50

55

